



Recycler Bag Material

Technical Data Sheet

	<u>Typical Value</u>
Tensile Strength at Yield, psi	10,900
Elongation at Fail, %	270
Elongation at Yield, %	9
Secant Modulus, psi	435,000
Melting point (DSC), °F	493
Deflection Temperature at 66 psi, °F	450
at 264 psi, °F	180
Specific Gravity	1.14
Yield for 1.0 mil, sq. in./lb.	24,285
Continuous Use Temperature, °F	450

*Values reported for 0.2% moisture.



2010 Cobb International Blvd Suite H Kennesaw, GA 30152
T (800) 655-5649 F (800) 655-5684 www.beccainc.com